Steinwall Inc.
Re-Defining the Supply Chain®
Working in Harmony with Our Customers
1759 116th Avenue N.W. Minneapolis, MN 55448-3028
Phone: (763) 767-7060 (800) 229-9199
Fax: (763) 767-7061
www.steinwall.com

ACRYLONITRILE STYRENE ACRYLIC ESTER (ASA)

1. Common trade names:	Centrex, Geloy CR, Luran S		
	UNITS		
2. Density	g/cm^3	1.06	Mass per unit volume
3. Mold Shrinkage	in./in.	.003-.006	Size of part versus mold cavity
4. Continuous Service Temp	°F	180	Highest temp material can perform reliably for the long term
5. Melting Point	°F	221	Tempurature material begins to melt
6. Processing Temp	°F	460-520	Recommended tempurature for molding
7. Tensile Strength	$\frac{lb}{in.^2}$	5600	Maximum stress without yielding to a stretching mold
8. Izod Impact Strength	$\frac{ft\text{-}lb}{in.}$	9	Energy required to break at a v-notch
9. Compressive Strength	$\frac{10^3\ lb.}{in.^2}$		Resist a crushing force
10. Flexural Strength, yeild	$\frac{10^3\ lb.}{in.^2}$	9	Resistance to fracture during bending
11. Elongation, tensile break	%	45	Stretching ability before breaking
12. Dielectric Strength	$\frac{V}{10^{-3}\ in.}$	813-1101	Voltage material can withstand before dielectric breakdown * = aluminum oxide
13. Water Absorption, 24 hours	%	.11-.32	% Water absorbed when immersed in water for 24 hours
14. Coefficent of Lin. Thermal Expansion	$\frac{10^{-5}\ in.}{in.\ °F}$	4.9-8.3	Change in length per change in temperature
15. Crystalline or Amorphous	C = Crystalline A = Amorphous	A	Crystalline: arranged polymer, sharp melting point Amorphous: random polymer, broad melt)
16. Clarity	O = Opaque TP = Transparent TL = Translucent	O	Opaque = no light passes through it Transparent = some light passes through it Translucent = light passes directly through it
17. Flammability	**Flame Resistance** **High ← Low** **5VA 5VB V-0 V-1 V-2 HB**	HB / V-1	Reference standard UL 94
18. Process: Drying Required		Yes	Is it recommended to dry the material prior to molding?
19. Hot Stamp			Does the material hot stamp?
20. Machining Qualities	**Qualitative Scale: Excellent, Good, Fair, Poor**	Good	How does the material machine?
21. Creep Resistance		Poor	Can this material keep it's shape under load? * = with additive or co-polymer
22. Ultrasonic Welding		Good	Does the material weld via ultrasonics?
23. Low Friction		Good	Surface lubricity
24. Abrasion Resistance		Poor	How well does the material withstand wear? * = with additive or co-polymer
25. Solvent Resistance		Good	How well does the material withstand chemicals?
26. UV Resistance		Excellent	How well does the material withstand UV rays? * = with UV additive
27. Environmental Stress Crack Resistance		Excellent	Can this material resist environmental stress cracking? * = with additive or co-polymer
28. FDA			Are there FDA grades available?
29. Living Hinge		No	Can this material be used in a living hinge application?
30. Year Developed		1970	
31.Cost: year 2006	$/lb. @ 5,000 lbs.	$4.77	Natural/Black Year 2006

32. Applications: **Weatherable, Color Stability, Auto Parts, Recreation, Marine**

© 2007 Steinwall Inc.